



lyondellbasell  
*Advancing Possible*



# Catalloy Process Resins

Key Properties and Applications

# Catalloy Process Resins

Properties	Physical		Mechanical				Charpy Notched Impact Strength	Typical Conversion Processes	Typical Customer Applications	Notes	
	Melt Flow Rate (2.16 kg, 230°C, g/10min) ISO 1133	Flexural Modulus (MPa) ISO 178	Tensile Stress at Break (MPa) ISO 527	Shore D Hardness (15 seconds) ISO 868	HDT (°C) (0.45 Mpa) ISO 75	VICAT (A50°C) ISO 306					(23°C) (kJ/m <sup>2</sup> ) ISO 179
<b>Adflex</b>											
Q108F	0.60	100	10	30	40	60	41	107	2.8	Automotive	Flexibility and softness
Q100F	0.60	100	10	30	40	60	NB	110	5	Flexible packaging	High impact, elastic recovery
Q401F	0.65	480	21	49	57	108	86	3.2	2.2	Flexible packaging	Stiffness and impact balance
Q402F	0.65	480	21	49	57	108	86	3.2	2.2	Flexible packaging	Stiffness and impact balance
Q200F	0.80	150	13	49	44	76	60	87	2.1	Flexible packaging	High impact
KS021P	0.90	350	10	38	52	67	70	98	3.2	Automotive, flexible packaging, industrial blow molding	Soft touch, matte finish
Q302B	0.90	350	10	38	52	67	70	98	3.2	Tubes, bottles	Soft touch, matte finish
X101H	8	100	10	30	36	55	NB	NB	1.5	Flexible packaging, bitumen modification	Flexibility and impact
X500F	7.5	550	22	46	58	94	65	45	5	Flexible packaging	Clarity impact modifier
KS311P	9.5	530	15	46	53	112	59	4.1	1.4	Roofing membrane, automotive	Soft touch, matte finish
V109F	12	80	8	30	35	55	35	5	1.4	Flexible packaging	Flexibility and impact
Z108S	27	80	6	30	37	53	33	2.8	1.3	Flexible packaging	Flexibility and impact
KS084P	30	100	13	35	40	53	47	2.8	1.2	Flexible packaging	Flexibility and impact
<b>Hifax</b>											
CA10A	0.60	90	11	30	40	60	NB	110	5	Roofing membrane, geomembrane, automotive	Flexibility and softness
X1956A	0.9	800	30	65	70	145	95	10	5	Automotive	Anti-tiger stripe additive
CA138A	2.8	500	10	41	58	90	70	100	50	Automotive	Low temp. Impact modifier
CA207A	7.5	550	22	46	58	94	65	45	5	Automotive	Low shrinkage
CA7442A	10	1000	17	54	86	121	50	10	4.5	Automotive	Low shrinkage
CA387A	18.5	1000	13	52	80	120	60	8.7	2.6	Automotive	Stiffness and low temp impact balance
7430XEP	18.5	1200	14	55	90	131	14	6.7	2.8	Automotive	Stiffness and low temp impact balance

# Catalloy Process Resins



Properties	Physical		Mechanical				Charpy Notched Impact Strength	Typical Conversion Processes	Typical Customer Applications	Notes			
	Melt Flow Rate (2.16 kg, 230°C) (g/10min) ISO 1133	Flexural Modulus (MPa) ISO 178	Tensile Stress at Break (MPa) ISO 527	Shore D Hardness (15 seconds) ISO 868	HDT (°C) (0.45 Mpa) ISO 75	VICAT (A50,°C) ISO 306					(23°C) (kJ/m2) ISO 179	(-20°C) (kJ/m2) ISO 179	(-40°C) (kJ/m2) ISO 179
<b>Softell</b>													
Grade Name	CA02A	0.60	30	10	23	38	41	NB	NB	9	Sheet extrusion, compounding, calendaring	Automotive, roofing membrane	Flexibility and softness
<b>Hiflex</b>													
Grade Name	CA7600A	2.0	180	11	26	45	58	NB	NB	110	Compounding, injection molding	Automotive	Impact modifier

Properties	Physical		Mechanical				Haze (50 µm) ASTM D1003	Gloss (45°, 50 µm) ASTM D2457	Typical Conversion Processes	Typical Customer Applications	Notes	
	Melt Flow Rate (2.16 kg, 230°C) (g/10min) ISO 1133	Flexural Modulus (MPa) ISO 178	SIT (°C) Internal Method	Tm (°C) Internal Method	HDT (°C) (0.45 Mpa) ISO 75	VICAT (A50,°C) ISO 306						
<b>Adsyl</b>												
Grade Name	6C30F	5.5	500	95	128	59	103	0.2	92	BOPP, Cast film	Flexible packaging	Sealing resin
	5C30F	5.5	600	105	132	62	107	0.6	88	BOPP, Cast film	Flexible packaging	Sealing resin
	5C37F	5.5	600	105	132	62	107	1.0	87	BOPP, Cast film	Flexible packaging	Sealing resin
	7416XCP	7.5	600	115	133	65	115	0.5	90	BOPP, Cast film	Flexible packaging	Sealing and bonding layer resin

Users should review the applicable Safety Data Sheet before handling the product. Technical Data Sheets (TDSs) and Safety Data Sheets (SDSs) are available at [www.lyb.com](http://www.lyb.com). For regulatory compliance information, see the applicable product's Product Stewardship Bulletin (PSB).

NB = No Break

# ABOUT US

**LyondellBasell (NYSE: LYB)** is one of the largest plastics, chemicals and refining companies in the world. Driven by its 13,400 employees around the globe, LyondellBasell produces materials and products that are key to advancing solutions to modern challenges like enhancing food safety through lightweight and flexible packaging, protecting the purity of water supplies through stronger and more versatile pipes, and improving the safety, comfort and fuel efficiency of many of the cars and trucks on the road. LyondellBasell sells products into approximately 100 countries and is the world's largest licensor of polyolefin technologies. In 2018, LyondellBasell was named to Fortune Magazine's list of the "World's Most Admired Companies."

**For more information, visit [lyb.com](http://lyb.com) or please contact:**

**Europe**

[EU.Polymers@lyb.com](mailto:EU.Polymers@lyb.com)

**North America**

[NA.Polymers@lyb.com](mailto:NA.Polymers@lyb.com)

**South America**

[SA.Polymers@lyb.com](mailto:SA.Polymers@lyb.com)

**Africa, Middle East, India**

[AFMEI.Polymers@lyb.com](mailto:AFMEI.Polymers@lyb.com)

**Asia**

[AP.Polymers@lyb.com](mailto:AP.Polymers@lyb.com)

**Australia/New Zealand**

[AU.Polymers@lyb.com](mailto:AU.Polymers@lyb.com)

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT. LyondellBasell prohibits or restricts the use of its products in certain applications. For further information on restrictions or prohibitions of use, please contact a LyondellBasell representative. Users should review the applicable Safety Data Sheet before handling the product.

*Adflex, Hifax, Softell, Hiflex, Adsyl and Catalloy* are trademarks owned and/or used by the LyondellBasell family of companies.

**lyondellbasell**  
*Advancing Possible*